

Charging Tables

Fluorescent charging of Ecoglo S10 Material (20 lux, 4000K) In A Poorly Lit Area	
Activation Time	Hours of Visibility*
5 minutes	0.5 hours
10 minutes	1 hours
20 minutes	2.25 hours
30 minutes	3 hours

** A luminance level of 5 millicandelas is defined as visible by NYC RS6.1 and ICC*

Fluorescent charging of Ecoglo S10 Material (150 lux, 4000K) In A Reasonably Lit Area	
Activation Time	Hours of Visibility*
5 minutes	2.5 hours
10 minutes	4 hours
20 minutes	6 hours
30 minutes	7 hours

** A luminance level of 5 millicandelas is defined as visible by NYC RS6.1 and ICC*

Fluorescent charging of Ecoglo S10 Material (300 lux, 4000K) In A Well Lit Area	
Activation Time	Hours of Visibility*
5 minutes	4 hours
10 minutes	6 hours
20 minutes	7 hours
30 minutes	8 hours

** A luminance level of 5 millicandelas is defined as visible by NYC RS6.1 and ICC*